Islamic University Journal of Applied Sciences (IUJAS)
https://journals.iu.edu.sa/jesc

Volume VIII, Issue I, July 2026, Pages 22-45

Magnetic Ferrite/TiO_2 Nanocomposites for Enhanced Photocatalytic Water and Air Remediation

Hossameldin G. Mohamedbakr[1],*, K F. Hassan[1], Medhat M. El-Moselhy[1], Mohamed S. Thabet[1] Zeinhom H. Mohamed[1] and Usama. A. Soliman[1]

[1] Chemistry Division, Department of Physical Sciences, College of Science, Jazan University, , P.O. Box. 114, Jazan, 45142, Kingdom of Saudi Arabia

*Corresponding author: (Hossameldin G. Mohamedbakr), hmohamedbakr@jazanu.edu.sa

Abstract

Melding ferrite nanoparticles into the TiO_2 semiconductor lattice endows ferrite/TiO_2 nanocomposites, with a two-fold capability: they can be magnetically retrieved and upon light exposure they break down contaminants. This dual action directly tackles pressing woes stubborn organic pollutants lingering in water and greenhouse gases hovering in the atmosphere by sharpening charge separation and stretching light absorption deeper into the visible spectrum. Moreover, the spinel ferrite's tunable cation arrangement reshapes both its electronic band structure and overall behavior thereby dictating efficiency and the material's recyclability. A thin silica layer improves charge transfer and stability, while anatase–rutile–brookite TiO_2 mixtures enhance charge separation. These engineered photocatalysts degrade dyes and pharmaceutical pollutants in water and also drive hydrogen production through photocatalytic water splitting. Thanks, to their nature retrieving the catalyst is straightforward which curtails waste and trims operational expenditures. Taken together the nanocomposites chart a path toward environmental remediation and renewable power generation marrying photocatalytic prowess, with magnetic pull for straightforward recovery.

Keywords: Magnetic ferrite/TiO_2 nanocomposites, photocatalysis, water remediation, air purification, charge separation and visible light absorption.


https://doi.org/10.63070/jesc.2026.015
Received 16 November 2025; Revised 23 January 2026; Accepted 14 February 2026.
Available online 04 March 2026.
Published by Islamic University of Madinah on behalf of *Islamic University Journal of Applied Sciences*.
This is an open access article published under the Creative Commons Attribution 4.0 International license (CC BY 4.0):https://creativecommons.org/licenses/by/4.0/

1. Introduction

Ferrite/TiO_2 nanocomposites belong to a material family that fuses magnetic ferrite nanoparticles with the semiconductor titanium dioxide endowing the composite with both magnetic and photocatalytic traits. The motivation for this marriage is straightforward: ferrites deliver a high saturation magnetization, which makes separation after a reaction virtually effortless while TiO_2 contributes potent photocatalytic activity under UV or solar light enabling the degradation of pollutants, in aqueous environments[1, 2]. This synergy reshapes the composite into a platform that can both catalyst chemical reactions and be easily reclaimed, confronting efficiency and sustainability challenges in environmental remediation systems. The routes to prepare composites fall into two categories “top-down" and "bottom-up" approaches. In the approach bulk material is broken down into nanoscale particles using physical techniques such, as ball-milling or laser ablation which typically yields a polydisperse particle size distribution[3]. Conversely "bottom-up" synthesis relies on controlled chemical or solvothermal routes that enable precise tweaking of cation distribution and particle shape. This method is often preferred when the aim is to maximize surface area and improve interface quality because catalytic activity is highly sensitive, to how active sitesre dispersed. Nonetheless both approaches have their constraints; maintaining uniform particle size and a well-ordered cation arrangement is essential to preserve the desired magnetic properties while extracting the best photocatalytic performance. Viewing it from a material-science angle spinel ferrites are especially appealing because their crystal lattice readily welcomes dopants of either divalent or trivalent metal ions. Such doping simultaneously tweaks the electronic band structure in ways that boost activity and alters the magnetic anisotropy that facilitates easy separation[4]. Experimental work on mixed ferrite systems e.g. Zn–Ni ferrite embedded in freudenbergite has revealed an enhancement in breaking down dyes, like methyl orange and methylene blue when the material is exposed to light. The co-habitation of metal cations within a spinel matrix tends to broaden the catalytic response window and at the same time reinforce magnetic-recovery capabilities. In the arena TiO_2 enjoys a solid reputation for a relatively high quantum yield under UV irradiation a benefit that springs from the electron-hole pairs it creates and that fuels redox reactions, on its surface. Still the naked form of TiO_2 is plagued by charge recombination. Embedding ferrites gives rise to heterojunctions (for example n-SnO_2/p-ferrite, architectures) where interfacial charge transfer lingers delaying recombination and boosting the photodegradation rate of organic pollutants[5]. Depending on how the ferrite’s band-gap aligns these heterojunctions can also pull the absorption edge into the spectrum making solar-driven water-treatment on a large-scale more practicable. The environmental target compounds that ferrite/TiO_2 photocatalysts set their sights on span dyes such, as the R250 hue, a gamut of phenolic constituents’ pharmaceutical agents exemplified by carbamazepine and the tangled stew of pollutants

found in complex industrial effluents[3, 6]. In runs degradation efficiencies tend to climb as time ticks by eventually levelling off; at a dye concentration of 100 ppm notable removal percentages have been reported when illumination is finely tuned to optimal conditions [3]. Notably when the system is kept in the dark the catalytic reactions scarcely move; the nanocomposites we crafted themselves show no activity under those conditions when tested against phenol-laden water[6]. highlighting that photoactivation is the driver. Magnetically recoverable nanocomposites also alleviate a flaw of many powder catalysts their clumsy removal from the treated water, which usually forces filtration steps that are prone, to choking. High-coercivity ferrites pose a risk of complicating demagnetization when they're recycled; for that reason, researchers have proposed low-coercivity alternatives such, as $SrFe_{12}O_{19}$ combined with TiO_2/SiO_2/graphene oxide where reversible magnetization enables reuse cycles without a substantial loss of catalytic capacity [1]. Sustainability arguments favour these designs because they cut down the secondary waste streams that typically arise from disposable single-use catalysts. Expanding the discussion past wastewater treatment researchers are now probing ferrites for biomedical uses. In hyperthermia nanoparticles of Fe_3O_4, $CoFe_2O_4$ and $MnFe_2O_4$ are harnessed to produce localized heating under alternating magnetic fields a consequence of their magnetic losses [4] . Though this medical avenue pursues objectives that differ starkly from those of photocatalysis it underscores the remarkable flexibility of ferrite materials. Looking at the problem, from a perspective the lessons learned about steering crystallinity and particle interfaces in one arena could very well inform the other. Surface chemistry matters as much; zeta-potential measurements reveal how electrostatic forces steer the deposition sequence first laying down a silica interlayer on a ferrite core and then adding a TiO_2 coating. These electrokinetic characteristics shape colloidal stability throughout the synthesis and dictate the uniformity of the shell's thickness[6]. Designed core-shell structures not only guard the magnetic phase against corrosion but also maximize the contact between pollutant molecules and the reactive TiO_2 facets, during illumination. Taken as a whole the design ethos behind ferrite/TiO_2 nanocomposites is a hybrid marrying the pull of magnetism which makes recovery a breeze with the push of semiconductor chemistry, which drives transformation. Fine-tuning these hybrids demands a trade-off among a suite of structural variables: how broadly the particle sizes are distributed, which cations populate the ferrite lattice, how uniformly the TiO_2 coating blankets the particles, the degree of coercivity tweaking required for easy recyclability and the quality of the heterojunction, at the interface that governs efficient charge-separation kinetics. Synthesizing insights from several investigations [1, 3, 5]with a deliberate engineering strategy these hybrid platforms appear as versatile candidates, for confronting the worldwide water-pollution challenge marrying robust contaminant degradation with energy-frugal recovery techniques.

Schematic 1: magnetic Ferrite/TiO_2 nanocomposites for enhanced photocatalytic water and air remediation




2 – Digging into the Background Uncovering Its Significance.

2.1 Environmental predicaments that photocatalysis can assist in resolving.

2.1.1 Water contamination sparked by a cocktail of compounds.

The worsening environmental pollution crisis driven by industrial waste streams, pharmaceutical residues and pesticide runoff calls for cutting-edge, sustainable cleanup methods. One promising avenue is photocatalysis, where light energy powers the oxidative breakdown of contaminants. In this arena titanium dioxide (TiO_2) stands out; it has been examined extensively because of its oxidizing ability, solid chemical stability, low cost and inherent non-toxicity[7, 8]. Nonetheless the mass deployment of TiO_2 collides with a pair of entrenched limitations: its expansive bandgap fences its photo-responsiveness to the ultraviolet (UV) fringe of sunlight just, about 4-5 % of the solar spectrum and the fleeting existence of photogenerated electron-hole pairs, which recombine so swiftly they whittle away its quantum efficiency[9, 10].

Figure 1 : Ferrite/TiO_2 nanocomposites



The allure of Ferrite/TiO_2 nanocomposites stems from an engineering trick: they not only patch the usual drawbacks of TiO_2 photocatalysts but also slip in a prized new trait magnetism. When a magnetic

ferrite think $CoFe_2O_4$, $CuFe_2O_4$ or $NiFe_2O_4$ is paired with TiO_2, the resulting behaves, like a synergistic team. Consequently, the photocatalytic window widens into the visible-light region. The catalyst can be coaxed out of the treated water with a simple external magnet making recovery a breeze. By confronting an operational bottleneck in slurry-based photocatalytic systems this work clears a path toward economical and reusable technologies, for environmental remediation [4, 6, 8]. The latest surveys have catalogued about 1×10^5 toxic chemical species detectable, across a diverse array of water sources worldwide. Among the contaminants synthetic dyes, pesticides and pharmaceutical residues stand out for their persistence and ongoing biological activity. Their ubiquity isn't accidental; the textile sector for example pumps out roughly 10^4 dyes annually a total that tops 7×10^5 tones entering the environment [7]. Such staggering quantities inevitably load the ecosystem because even the faintest traces of dyes can tint water, curtail penetration interfere with photosynthesis and upset the balance of aquatic habitats. The dogged persistence of pollutants traces straight to the intricacy of their molecular scaffolds. Synthetic dyes for example are packed with interlocking ring systems and a tangled lattice of double bonds endowing them with a stubborn resistance, to the degradation pathways nature normally exploits. Likewise, many pharmaceuticals bear halogen-laden substituents or fused heterocyclic frameworks that further thwart breakdown. As a result, conventional wastewater-treatment schemes that depend on separation or biological digestion often stumble when they confront these recalcitrant molecular backbones. Then being fully broken down into harmless CO_2 and H_2O many of these compounds stall halfway leaving behind partial degradation products that can prove even more toxic than the original molecule. This lingering persistence drives bioaccumulation in organisms, which then pass up the food chain. To make matters worse effluents seldom contain one type of contaminant. Wastewater from textile factories, for example is a cocktail of azo dyes, dispersants, surfactants and heavy metals. When runoff from farms spills, into lakes, rivers or streams it delivers a cocktail of pesticides, nitrogen-rich fertilizers and herbicides. The way these chemicals mingle can dramatically reshape their fate sometimes they accelerate degradation through synergistic interactions other times they retard it via antagonistic effects. For instance, mixtures of contaminants can alter adsorption onto particles or nanomaterials because they vie for the reactive sites thereby shifting binding affinities. Photocatalysis has risen as an oxidation method that attacks these molecules producing potent reactive oxygen species whenever light energizes semiconductor catalysts like TiO_2. Yet in its bare form TiO_2 suffers from poor charge separation because photogenerated electrons and holes tend to recombine, which dramatically limits its efficiency. Tailoring the catalyst surface with compounds can slow this recombination and as a bonus can endow the material, with magnetic traits that simplify its recovery after use. At glance it appears mainly as a catalyst-recycling upgrade yet it also accelerates overall treatment throughput because a quicker regeneration step trims

the downtime between remediation cycles. The urgency of the problem becomes starkly evident when one examines case studies that use model pollutants. Methyl orange (MO) methylene blue (MB) and the R250 dye are frequently employed as contaminants, in evaluating remediation approaches since they mirror the characteristics typical of real effluent streams. When the initial concentrations are relatively high 100 ppm for instance the photocatalytic rate can collapse if the catalyst dose is too low. This deceleration stems from dye molecules hoarding photons, which compresses the light-penetration depth in the reaction medium and simultaneously occludes sites on the catalyst [11]. Reducing the catalyst dosage while ramping up the load aggravates the problem as it throttles the generation of electron-hole pairs, per irradiated volume. Even though many different contaminants often travel down oxidative degradation routes such as the breaking of azo bonds in dye molecules their reaction rates can vary dramatically governed by pH the presence of co-contaminants and the particular surface chemistry of the catalyst employed[12]. A number of studies that couple UV-C radiation with anatase TiO_2 have demonstrated that dye-removal efficiency is tightly tied to alkaline conditions ($pH \approx 10$) because such an environment triggers a pronounced spike, in formation. Hand-visible-light-active composites such as ZrO_2/Ag-TiO_2 have proven capable of slashing up to 90 % of pollutants AZT being a notable example within eight hours under, neutral-pH conditions. This performance hints that by tweaking the illumination wavelength and reshaping the architecture the approach could be broadened to tackle a much wider spectrum of contaminants. Beyond the chemical hazards untreated organic waste also leaves a visual scar cloudy water, odd hues that can tarnish a water body's reputation and erode its economic value. In tourism-dependent regions a river or coastal stretch that suddenly takes on a hue from effluent can devastate local livelihoods even when measured contaminant levels technically sit within nominal safety limits. Moreover, prolonged low-dose exposure, to these compounds has been linked to endocrine-disrupting effects and a rising cancer risk endangering both wildlife and the people who draw drinking water from the source. Confronted with this challenge remediation strategies must prioritize not just raw degradation efficiency but also the capacity to adapt to shifting influent characteristics over time. Real wastewater plants are anything but steady pollutant loads can swing from day to day echoing production timetables or seasonal agricultural rhythms [4]. Hence a photocatalyst's value hinges on its knack, for preserving performance without the baggage of pre-conditioning, even as those loads dance unpredictably. Seen through the prism of probing water contamination by compounds the quest is inseparably bound to forging catalytic materials that can deftly tackle a kaleidoscope of molecular shapes whether the targets are textile-derived chromophores flaunting extensive π-systems or hydrophobic pharmaceutical scaffolds that cling readily to microplastics as they drift through waterways[13]. The multifaceted nature of ferrite/TiO_2 composites hands engineer a route for contaminant removal merging physicochemical pathways: a heightened

light-driven oxidation coupled with a simple magnetic pull-out. This tandem not accelerates the primary degradation but also damps the formation of secondary pollutants that frequently hitch a ride, with clean-up schemes that lean on bulky flocculant dosages or the painstaking back-wash of membrane filters. Even as researchers keep honing these catalysts navigating obstacles such, as a light-absorption band or fouling from natural organic matter the core impetus remains unchanged: to grapple with the tenacious complex organic pollutants that still inundate freshwater supplies worldwide.

2.2.2 Complications, in Charge-Carrier Recombination


Photocatalysis relies on the generation of electron–hole (e^-/h^+) pairs upon light absorption and their subsequent migration to surface reaction sites. In TiO_2-based photocatalysts, however, rapid recombination of these carriersoften occurring on nanosecond timescales represents a dominant loss pathway, dissipating absorbed photon energy as heat or radiative emission rather than driving redox reactions. This intrinsic limitation substantially constrains the quantum efficiency of pristine TiO_2 systems. [8,14]. This intrinsic recombination remains one of the principal bottlenecks in TiO_2 photocatalysis. Photocatalysis relies on the generation of electron–hole (e^-/h^+) pairs upon light absorption and their subsequent migration to surface reaction sites. In TiO_2-based photocatalysts, however, rapid recombination of these carriers often occurring on nanosecond timescales represents a dominant loss pathway, dissipating absorbed photon energy as heat or radiative emission rather than driving redox reactions. This intrinsic limitation substantially constrains the quantum efficiency of pristine TiO_2 systems.

The formation of ferrite/TiO_2 heterojunctions has emerged as an effective strategy to suppress recombination by promoting spatial charge separation. As illustrated schematically in **Figure 2**, two distinct charge-transfer configurations are commonly discussed: Type-II and Z-scheme heterojunctions. In Type-II systems (Figure 2a), electrons and holes migrate to different semiconductor phases, reducing recombination probability but simultaneously lowering the redox potentials of the surviving carriers. While this configuration improves charge separation, it often compromises oxidative and reductive driving forces.

In contrast, Z-scheme ferrite/TiO_2 heterojunctions (Figure 2b) selectively recombine low-energy electrons and holes at the interface, leaving high-energy electrons in the TiO_2 conduction band and strong oxidizing holes in the ferrite valence band. This mechanism preserves redox strength while prolonging carrier lifetimes, thereby enhancing photocatalytic efficiency under both UV and visible-

light irradiation. The superiority of Z-scheme architectures in balancing recombination suppression and redox activity explains their frequent adoption in ferrite/TiO_2 composite designs.

Figure 2: a) Type-II and b) Z-scheme heterojunctions



a b

Despite these advantages, recombination cannot be entirely eliminated. several operational factors contribute to performance degradation over time. Lattice mismatch at the ferrite–TiO_2 interface can generate strain fields that evolve into dislocations, which act as defect-mediated recombination centres during prolonged irradiation. Surface fouling by reaction intermediates or strongly adsorbed pollutants further exacerbates recombination by blocking active sites required for effective charge utilization. Coupling TiO_2 with ferrite semiconductors to form heterojunctions has proven effective in suppressing recombination. Favourable band alignment at the interface generates an internal electric field that promotes spatial charge separation. In Z-scheme ferrite/TiO_2 systems, such as $CoFe_2O_4$/TiO_2, electrons in the ferrite conduction band preferentially recombine with holes in the TiO_2 valence band, leaving highly energetic electrons in the TiO_2 conduction band and holes in the ferrite valence band. This configuration preserves strong redox potentials while extending carrier lifetimes, thereby enhancing photocatalytic activity under both UV and visible light [4,15]. Similar improvements have been reported for TiO_2/$CuFe_2O_4$ architectures, where efficient charge separation significantly enhances pollutant degradation efficiency [10].

Despite these advantages, heterojunction systems are susceptible to performance degradation during prolonged operation. Lattice mismatch at the ferrite–TiO_2 interface can generate strain that evolves into dislocations, which act as recombination centres under repeated irradiation cycles. Additionally, surface fouling by reaction intermediates or strongly adsorbed pollutants can block active sites, redirecting charge carriers toward recombination pathways [6]. Particle aggregation represents another challenge, particularly for magnetic ferrite-based composites. Dipole–dipole interactions between

magnetic cores promote agglomeration, reducing effective surface area and increasing local carrier density, which in turn accelerates recombination [5]. Thin silica interlayers have been introduced to mitigate aggregation by physically separating particles while still permitting tunnelling-assisted charge transfer. However, excessive interlayer thickness impedes carrier mobility and suppresses interfacial redox reactions [6].

The stoichiometry of the ferrite phase further influences recombination dynamics. Adjusting cation composition alters band structure and interfacial charge transfer; for example, increasing Co^{2+} content relative to Zn^{2+} has been shown to prolong charge-separation lifetimes and improve photocatalytic performance [4]. Over-substitution, however, may introduce defect states or induce phase segregation, counteracting recombination suppression by creating additional non-radiative pathways. From a kinetic perspective, recombination reduces the effective rate constants of oxidation and reduction half-reactions by depleting the pool of reactive carriers below the threshold required for sustained radical-mediated degradation. This behaviour explains the commonly observed performance plateau in dye and pollutant degradation studies, where initial rapid removal is followed by a marked decline despite continuous illumination [3]. In contrast, optimized systems such as CuCe-ferrite/TiO_2 demonstrate near-complete degradation within short reaction times by maintaining prolonged charge separation at heterojunction interfaces. Recombination suppression can be conceptually described by maximizing the carrier lifetime (τ_s) and mean free path (l_s), according to:

$$R_{rec} \propto 1 / (\tau_s \cdot l_s)$$

Accordingly, rational catalyst design through controlled band alignment, interfacial engineering, dopant optimization, and aggregation management remains essential for reducing recombination losses and translating laboratory scale efficiencies into practical photocatalytic applications. While ferrite/TiO_2 composites offer multiple pathways to mitigate recombination, careful optimization is required to avoid trade-offs that hinder charge mobility or suppress reactive species generation.

3. Ferrite Materials, in Photocatalysis

3.1 Delving, into the Spinel Ferrite Crystal Structure

Ferrites metal oxides invariably adopt the MFe_2O_4 framework, where M denotes a divalent metal cation such as Fe^{2+}, Co^{2+}, Ni^{2+}, Cu^{2+}, Zn^{2+} or any mixture of these. Their appeal, in applications stems from a handful of standout characteristics:

Narrow Bandgap: Ferrites feature a bandgap in the 1.5–2.5 window a sweet spot that lets them harvest visible photons with impressive efficiency [8, 14]. Leveraging these formulations that embed ferrite particles can markedly boost TiO_2's photo-activity across the visible spectrum. ferrites the composite

gains magnetic separability, turning the retrieval of the photocatalyst for reuse, into a straightforward task a conclusion supported by numerous reports [3, 16, 17].In many frameworks metal cations tend to serve as co-catalysts upping surface reactivity and coaxing oxidants peroxymonosulfate (PMS) being a key example into forming the energetic sulfate radical ($SO_4^{\bullet-}$) [7, 10, 18].Choosing an M^{2+} cation opens the door to tweaking the composite's magnetic traits. Cobalt ferrite ($CoFe_2O_4$) finds application, its pronounced coercivity coupled with resilient chemical stability positioning it as a pivotal constituent, within Z-scheme photocatalytic constructs that facilitate CO_2 reduction while simultaneously decomposing dye molecules [4, 6, 19].Copper ferrite ($CuFe_2O_4$) and its kin, such as CuCe-ferrite turn out to be surprisingly effective at stripping color from dyes and breaking down pesticides a performance that originates from copper's redox hopping, between Cu^+ and Cu^{2+} ions [3, 10].Nickel ferrite ($NiFe_2O_4$) has found a niche in composites. Is also quite effective, at photodegrading dyes [16, 20]Both barium ferrite ($BaFe_{12}O_{19}$) and its strontium counterpart ($SrFe_{12}O_{19}$) sit snugly within the material family. In practice they're frequently woven into matrices, where they serve as microwave-absorbing agents and simultaneously kick-start advanced oxidation processes [1, 21, 22]. Inverse spinels $NiFe_2O_4$ being a textbook example feature an occupancy: half of the Fe^{3+} cations nestle in the tetrahedral A sites whereas the balance of the Fe^{3+} ions together with all Ni^{2+} cations are relegated to the octahedral B sites[16]. Vibrational spectroscopy offers a glimpse into this structural blueprint. In the FT-IR spectrum the absorption shoulders that cluster between 580 and 573 cm^{-1} can be traced back to the stretching of the M_Td–O bonds i.e. the dance of oxygen against metal ions, in a tetrahedral coordination sphere. The band cluster, in the 396–390 cm^{-1} window is a fingerprint of stretching motions of bound cations i.e. the M_OH–O bonds [9, 23]. The precise displacement of these absorptions correlates with which metal occupies the site and how large its ionic radius is. In magnesium ferrites the high-frequency tetrahedral stretch is chiefly driven by Fe–O, Mg-O and when zinc is present Zn-O bonds, whereas Co-O and Ni-O whose strong propensity is, for sites predominantly shape the lower-frequency band. Strong site preference steers the morphology of nanoscale particles: Co/Ni-rich systems tend to generate the particles their occupancy buttressing condensed lattice domains; Mn-containing ferrites settle at an intermediate size (15 nm) reflecting a willingness to occupy both site types[4]. The cation distribution between A and B sites isn't a fixed attribute it can shift under treatment. Annealing at temperatures promotes greater ordering, within the cation sublattice. A striking illustration comes from ferrites. When these are annealed modestly around 950 °C their saturation magnetization tends to fall. Pushing the temperature up to about 1250 °C flips the trend and the magnetization rises again. The higher heat drives the cations to reorganize into an inverse spinel pattern that's more favorable for magnetic alignment[24].

3.2 Magnetic affect photocatalysis.

Magnetic properties in ferrite-based photocatalysts do more than simply enable post-reaction recovery; they can quietly modulate the process itself by affecting charge-carrier dynamics stabilising particle dispersion and even tweaking light-absorption behavior. Ferrites such as Fe_3O_4, $CoFe_2O_4$ or $BaFe_{12}O_{19}$ when incorporated into TiO_2 matrices impart a saturation magnetisation (M_s) that hinges not on the ferrite phase but also on structural tweaks such as coatings, with non-magnetic layers. When silica or titania shells are deposited onto cores, the measured saturation magnetization (M_s) drops relative, to the uncoated material simply because the added non-magnetic coating inflates the total mass. Intriguingly X-ray fluorescence analysis often reveals that this decrease is modest roughly a 14 % reduction compared with bare magnetite confirming that the ferrite core stays essentially intact despite the coating. Preserving that magnetization is vital since letting M_s fall below a threshold would compromise the efficiency of magnetic separation after the photocatalytic step. Viewed through a lens, coercivity (Hc) and remanence (Mr) emerge as pivotal factors for recyclability and stability, in photocatalysis. Magnetic hysteresis measurements reveal that when particle dimensions lie within the single-domain window certain ferrite composites adopt a super-paramagnetic character exhibiting very low Hc and Mr values [6]. Adjusting the process subtly reshapes the interaction strength among individual particles suspended in the liquid, which in turn nudges the zeta potential and dictates how close the particles can come before magnetic attraction overwhelms electrostatic repulsion. The sweet spot an optimum arises when electrostatic forces keep the particles from clumping while the magnetic pull remains strong enough to enable efficient recovery. Recyclability data highlight where magnetism and catalytic efficiency intersect in practice. For example, recycling experiments with $CoFe_2O_4/TiO_2$ catalysts up to five cycles show a barely perceptible drop, in pollutant-removal performance. With carefully managed washing and drying steps the material sheds only about five percent of its mass each separation cycle [25]. Introducing zinc typically dampens anisotropy, which in turn pulls down coercivity. The net effect is that the particles become easier to remix for a light exposure though the trade-off may be a weaker ability to lock in long-lived carriers that benefit from tighter spin coupling. The surrounding environment adds another layer of complexity: the pH shifts and ionic-strength variations encountered in wastewater-treatment operations tweak both the surface-charge magnitude and the magnetic coupling, between catalyst grains. Under conditions the electrical double layers that coat the particles get squeezed curtailing the electrostatic repulsion that normally keeps them apart. Neglecting to adjust the saturation magnetization (Ms) enough leaves the particles prone to clump together which in turn blocks light and drags the photocatalytic efficiency down despite a theoretically favorable band structure. Ultimately reclaiming spent catalysts can shave off energy that would

otherwise be spent on filtration an approach that often succumbs to fouling yet this upside hinges on the particles maintaining a viable M_s throughout their service life without leaching or the ferrite cores crumbling under the relentless oxidative assault of repeated illumination cycles[26]. Encapsulating the cores, in a silica veil has shown promise in slowing photo dissolution while still preserving an acceptable M s. Steering clear of thick barrier layers is essential since they throw off the tunnelling distances electrons need to reach TiO_2 and wipe out the catalytic gains that careful interface design promises. In turn magnetic properties are woven into photocatalyst behaviour not just a handy handle for recovery. They influence recombination rates by shaping electronic structures dictate particle dispersion through a tug-of-war, between dipolar attractions and electrostatic repulsion determine thermal and mechanical durability across reuse cycles and might even lend a slight edge to light absorption via local electromagnetic field effects[6]. Constructing the ferrite/TiO_2 composite demands a panoramic appraisal of the myriad influences, at play so that the magnetic gains pursued never inadvertently shut off active site accessibility or throttle carrier mobility both of which underpin sustained photocatalytic efficiency.

4 Titanium Dioxide, in Photocatalysis

4.1 Anatase, Rutile and Brookite (The trio of TiO_2 polymorphs).

Titanium dioxide appears in three crystal modifications anatase, rutile and brookite each bearing distinct physicochemical traits that shape its photocatalytic character. In practice anatase and rutile have attracted the lion's share of attention mainly because their synthesis routes are comparatively straightforward and their performance benchmarks are well-charted[27]. Anatase adopts a structure and remains metastable at room temperature whereas rutile, also tetragonal but denser occupies the thermodynamically stable niche. Brookite carries an orthorhombic lattice that seldom appears in contexts owing to the need for finely tuned control over nucleation pathways during fabrication. From a standpoint anatase often takes precedence because its electron–hole recombination proceeds more slowly than that of rutile [25]. Titanium dioxide (TiO_2) remains the benchmark photocatalyst due to its unparalleled advantages. It primarily exists in three crystalline phases: anatase, rutile, and brookite. Anatase is generally considered the most photocatalytically active phase due to its higher Fermi level and slower charge carrier recombination rate [8, 14]. Defects perched at the boundary become trapping sites, slowing electron–hole recombination and thereby supplying more carriers, for photocatalytic reactions. Seeing mixed-phase systems, in action makes it obvious that a material often deemed inferior can actually play a role when it's embedded in a well-designed structure. Brookite however stays a bit of a puzzle high-purity samples are scarce and the phase tends to shift into anatase or rutile during heat treatment. Still brookite has proven to be an UV absorber and its orthorhombic

coordination may endow it with distinctive surface chemistry. Its conduction- and valence-band edges sit a shade apart from those of anatase or rutile hinting that unconventional heterojunction configurations could be crafted to expand the material's spectral responsiveness. Phase changes are tightly coupled to the synthesis route and calcination conditions. For example TiO_2 obtained via hydrolysis of titanium alkoxides typically yields anatase when the calcination temperature hovers, around 400–500 ∘C [25]. Pushing the heat beyond 600 ∘C sparks the nucleation of rutile domains and by 700 ^∘C or higher rutile usually dominates unless dopants are introduced to kinetically lock in the anatase phase[16]. The escalating pollution crisis driven by a surge of industrial effluents lingering pharmaceutical residues and pesticide runoff demands remediation approaches that are both cutting-edge and sustainably practicable. Heterogeneous photocatalysis, which captures energy to power the dismantling of contaminants has risen to prominence as a leading contender in this field. Within the family of photocatalysts, titanium dioxide (TiO_2) commands the share of attention thanks, to its formidable oxidative strength, chemical durability, low cost and non-toxic character [8, 14]. The ambition to embed TiO_2 on a large scale runs into two persistent hurdles: an excessively wide bandgap that confines its activity, to the UV slice of sunlight barely 4–5% and the swift recombination of photogenerated electron-hole pairs, which saps its overall quantum efficiency [9, 10, 28].

Ferrite/TiO_2 nanocomposites stand out because clever engineering mitigates their drawbacks while adding an unexpectedly useful trait: magnetism. By coupling a ferrite such, as $CoFe_2O_4$, $CuFe_2O_4$ or $NiFe_2O_4$ with TiO_2 a synergistic composite is formed. This union not pushes the photocatalytic activity further into the visible-light range but also makes it possible to separate and recover the catalyst from treated water with a simple external magnet. By tackling a snag in slurry-based photocatalytic systems this work clears a pathway toward cheap reusable technologies, for environmental cleanup [6, 8].

4.2 Activation Using UV Light.

Historically TiO_2 has enjoyed a reputation as an efficient photocatalyst whenever ultraviolet light shines on it thanks to its broad bandgap and formidable oxidative power[29]. Yet relying solely on UV to fire up the reaction introduces a bottleneck, for harnessing solar energy since ultraviolet radiation makes up only about 3–5 % of the sunlight that reaches Earth's surface. In practice this imposes a bottleneck on any natural-sunlight-driven process forcing UV-based catalytic systems to either resort to high-intensity artificial illumination or to endure markedly longer reaction times to reach comparable pollutant-degradation levels. The anatase phase of TiO_2 with its bandgap hovering around 3.2 eV primarily captures UV photons; its rutile counterpart squeezes the gap down to 3.0 eV yet this modest narrowing still leaves it far, from the bandgap required for efficient visible-light activation[30]. When the system is driven by UV light, the photogenerated electrons that climb into the conduction

band together with the holes left in the valence band spark redox reactions capable of fully mineralizing complex organic molecules into harmless CO_2 and H_2O. Yet this tactic squanders the visible portion of sunlight essentially throwing away the lion's share of ambient solar energy. Moreover, restricting activation, to UV photons also imposes a selectivity shaping how the reactions proceed. Robust oxidative agents such as hydroxyl radicals (·OH) and superoxide anions ($\cdot O_2^-$) generated by TiO_2 under UV illumination act as oxidants, capable of dismantling a vast array of chemical structures [30, 31].

5 Ferrite/TiO_2 Nanocomposites.

5.1 Interface Engineering.

The photocatalytic performance of ferrite/TiO_2 nanocomposites isn't the sum of its parts; it's largely dictated by the atomic-level interactions at the interface, between ferrite and TiO_2. Interface engineering means deliberately designing and tweaking that junction to steer charge carriers improve stability and ultimately push photocatalytic efficiency to its peak. The goal is to craft a seamless intimate electronically coupled heterojunction that strongly suppresses charge recombination and eases reactions.

Where ferrite and TiO_2 encounter each other lies the interface a corridor linking two distinct semiconductors. The way their energy bands the apex of the valence band and the floor of the conduction band align in this space dictates what becomes of the electrons (e^-) and holes (h^+) generated by light. When the junction is deliberately engineered the resulting internal electric field can be coaxed to shepherd these charge carriers apart enhancing their separation.

In an arrangement with staggered band structures illumination causes electrons to cascade from the higher-lying conduction band into the lower one while holes drift from the upper valence band down, to its lower counterpart. This spatial partitioning of the photogenerated carriers effectively suppresses recombination. In the hybrid used for 2,4-D degradation the prevailing view is that photogenerated electrons residing in the $CuFe_2O_4$ conduction band migrate into TiO_2 while holes created in TiO_2's valence band move in the opposite direction, toward $CuFe_2O_4$. This bidirectional charge transfer, which effectively separates electrons and holes is identified as the primary driver of the markedly enhanced photocatalytic activity [10]. Likewise, the superior dye-decolorization observed with MnCo-Ferrite/TiO_2 and CuCe-ferrite/TiO_2 composites is ascribed to the interfacial charge-separation mechanism[3, 17, 32].

What emerges is an advanced generally more efficient approach that emulates natural photosynthesis. In a Z-scheme the low-energy electrons lingering in the TiO_2 conduction band bearing weaker reducing power pair up with the low-energy holes in the ferrite valence band possessing weaker oxidizing power

right, at their interface. Consequently the high-energy electrons stay in the ferrite conduction band while the strongest holes remain in the TiO_2 valence band poised to drive the reactions. This scheme has been explicitly examined for Ferrite/TiO_2-nanocomposites employed in CO_2 conversion. The investigation revealed a link, between the Co-Zn metal composition of the ferrite and its catalytic performance a relationship that directly reshapes the band structure and boosts the efficiency of the Z-scheme charge-transfer pathway at the interface [4].Consequently the system retains redox potentials while delivering outstanding charge separation.

These employed techniques let TiO_2 nucleate and grow straight onto pre-formed ferrite nanoparticles resulting in a core-shell or tightly bonded architecture. For example, TiO_2-$CoFe_2O_4$ and TiO_2-$CuFe_2O_4$ composite films have been prepared through a route that relies on the thermal decomposition of metal-organic precursors, a process that yields a uniform distribution and strong interfacial adhesion[9]. Whether the ferrite particles are cultivated within a TiO_2 matrix or the oxide is deposited onto the ferrite the method guarantees contact area, between the two phases. The Ni ferrite/TiO_2 nanofibrous composite was produced by electrospinning, entrapping the ferrite precursors within a TiO_2-polymer fiber matrix; calcination then fuses everything into an interwoven architecture [16]. With this progress several hurdles remain. Achieving pinpoint control over the atomic arrangement suppressing defect sites that serve as recombination traps and definitively establishing the charge-transfer pathway whether it follows a Z-scheme or a Type-II mechanism are far, from easy tasks. Future research directions include:

Doping at the Interface: Introducing dopants (Ce [13]) directly at the interface to establish "bridge" energy levels that further promote charge transfer. Construction of Multi-Component Interfaces: Adding a material such, as graphene or other semiconductors (e.g., GO-doped systems [1, 31]) to build multi-interface structures that can precisely steer charge separation and provide conductive pathways. Advanced Characterization: By harnessing in-situ techniques we can watch the charge dynamics and chemical environment at the ferrite/TiO_2 interface unfold in time as photocatalytic reactions proceed.

All things considered it’s the interface that truly holds the key to crafting high-performance ferrite/TiO_2 nanocomposites. When researchers move past the habit of merely mixing the powders together and instead meticulously design a nanoscale heterojunction, they unlock the full punch of these materials paving the way, for efficient down-to-earth environmental remediation.

5.2 Charge-Transfer Mechanisms in Ferrite-TiO_2 Nanocomposites.

The remarkable photocatalytic efficiency of Ferrite/TiO_2 nanocomposites is attributed to a series of rapid charge-transfer events occurring across the heterojunction interface. Understanding these events

how light generates electron-hole pairs, how charges separate, move, and are eventually utilized is crucial for any material design initiative. The referenced studies delineate the fundamental mechanisms and the variables influencing them.

The dynamic synergy between ferrite and TiO_2 establishes a pathway for charge migration, with academic literature identifying two primary mechanisms. The standard model of charge transfer is essentially based on band alignment. In a ferrite/TiO_2 composite, the conduction band (CB) and valence band (VB) of narrow-bandgap ferrites, such as $CuFe_2O_4$ or $CoFe_2O_4$, are situated at higher energy levels than the corresponding bands in TiO_2.Both semiconductors act as photon absorbers; ferrite is excited by light, while TiO_2 remains inactive unless exposed to ultraviolet photons. Electrons in the ferrite's high-energy conduction band find a lower-energy state in TiO_2's conduction band and migrate across the interface. Concurrently, photogenerated holes in TiO_2's valence band move into the higher-energy valence band of the ferrite. This leads to a spatial separation of charge carriers electrons accumulate in TiO_2 while holes remain in the ferrite significantly reducing the likelihood of recombination. This mechanism frequently explains the activity observed in systems such as MnCo-Ferrite/TiO_2 and CuCe-ferrite/TiO_2 composites, which can decolorize dyes under light, a performance attributed to a Type-II charge flow that effectively separates charges [3, 17].

Direct Z-Scheme Mechanism, This mechanism carefully maintains the high redox potential of each component. In a Z-scheme, the interfacial region acts as a conduit, facilitating the recombination of charge carriers that have minimal impact on performance. Photons excite both semiconductor layers. Electrons in TiO_2's conduction band, with reducing power, move to the neighboring semiconductor's band and pair with holes in the ferrite's valence band, which exhibit weak oxidizing ability at the interface. Post-recombination, the ferrite's conduction band retains high-energy electrons, while TiO_2's valence band accumulates potent holes. The system surprisingly maintains both reducing and oxidizing abilities simultaneously while achieving charge separation, useful for high-energy reactions such as CO_2 reduction. This mechanism is supported by research on Co-Zn ferrite/TiO_2 nanocomposites used for CO_2 conversion, where metal composition is linked to performance, indicating that tuning the ferrite's band structure directly influences Z-scheme charge-transfer efficiency[4]. The redox potential serves as a distinctive indicator of this pathway.

Ferrite as an Electron Pump and Sensitizer, In visible-light-driven catalysis, ferrite functions as a photosensitizer. Visible light excites the material, leading to electron-hole pair formation. Electrons are transferred from the ferrite's conduction band to TiO_2's conduction band, loading TiO_2 with electrons even though it does not need to absorb light. This process transforms wide-bandgap TiO_2 from a semiconductor into a light-driven catalyst, enabling electrons in TiO_2's conduction band to

reduce O_2 and generate superoxide radicals ($\bullet O_2^-$).This sensitizing effect is key to the activity observed in composites like Ni-ferrite/TiO_2 nanofibrous composite and $TiO_2/CuFe_2O_4$[10].

5.3-Enhancing Dynamics through Defect Engineering and Dopants.

Slight doping-induced modifications of an interface's structure can tailor charge flow, doping with cerium (Ce) introduces energy states within the bandgap. These energy levels act as a conduit for charge carriers, improving multi-step transfer efficiency over direct jumps, and trapping electrons or holes to further reduce recombination. Magnetic TiO_2 doped with cerium shows enhanced performance, and Ce^{3+}-doped Ni-Zn ferrite/TiO_2 composites exhibit significant behavioral improvements [13, 20, 23]. In both systems, cerium species act as charge-transfer mediators, accelerating charge separation at the interface.

Synergistic Charge-Transfer in Oxidation Processes (AOPs Peroxymonosulfate (PMS) activation weaves charge-transfer dynamics into a photochemical cycle.Photochemical Activation: Light-excited TiO_2 or ferrite generates electrons that directly activate persulfate via the pathway


$$HSO_5^- + e^- \rightarrow SO_4\bullet^- + OH^-.$$

Catalytic Activation, Metal ions within the ferrite, such as Co^{2+}/Co^{3+} and Cu^{2+}/Cu^+, efficiently decompose PMS.

Dynamic Synergy: The heterojunction acts as a source of electrons (or holes), sustaining the metal-ion redox cycle. For instance, electrons transferred to TiO_2 can reduce Co^{3+} to Co^{2+}, facilitating efficient catalytic PMS activation. Studies show synergy in TiO_2/Fe_2O_3/Chitosan [18] for degradation and $CoFe_2O_4$/Gr [7] for amoxicillin breakdown. The heterojunction's ability to separate charge carriers is closely linked to sulfate radical ($SO_4\bullet^-$) generation.

The charge-transfer dynamics in Ferrite/TiO_2 nanocomposites cannot be simplified into a single pathway; rather, they unfold as a multifaceted synergistic interaction with competing routes. The prevalence of either a Type-II cascade or a Z-scheme depends on the ferrite formulation, the synthesis method shaping interfacial quality, and the specific photocatalytic reaction under investigation. Thus, the ultimate goal of interface engineering is to direct these dynamics so that reactive charge carriers not only persist longer but also concentrate at the surface, enabling highly efficient pollutant degradation.

Schematic 2: The Self-Sustaining Cycle of a Magnetically Recoverable Ferrite/TiO_2 Photocatalyst



6. Real-world uses of Ferrite/TiO_2 nanocomposites.

6.1 Organic Pollutants Break Down in Water.

The synthesis of these composites involves various methods, including sol-gel, co-precipitation, hydrothermal processes, and electrospinning, to ensure an intimate contact between the ferrite and TiO_2 phases, which is crucial for efficient charge transfer [9, 27, 33]. Synthetic dyes are often chosen as stand-in pollutants in laboratory studies because they are vividly colored and chemically varied. In practice methylene blue (MB) and crystal violet (CV) serve as model substrates, for assessing photocatalytic performance. In visible-light-driven degradation trials TiO_2 catalysts loaded with nickel ferrite showed a striking uptick in pseudo-first-order rate constants compared with bare TiO_2. The boost is mainly credited to the inverse-spinel $NiFe_2O_4$ phase, which damps electron-hole recombination [10]. This isn't a lab-side note; real textile effluents often contain dye levels above 100 ppm and fast breakdown is crucial, for reinstating water quality before discharge. When the apparent reaction rate climbs under light the system taps solar irradiation more efficiently thereby mitigating a key drawback of UV-only activation setups [23]. Pharmaceuticals constitute another class of pollutants that ferrite/TiO_2 can tackle. In experiments with sulfamethoxazole (SMX) antipyrine (AP) and ibuprofen (IBP) $CoFe_2O_4/TiO_2$ catalysts achieved near-complete removal and their catalytic activity remained essentially unchanged, over five reuse cycles [34]. Recyclability here hinges on retrieval by snatching the catalyst out magnetically loss between runs is virtually eliminated and the surface stays free of fouling. The sturdiness of these hybrids traces back to an interfacial strategy: a feather-thin SiO_2 sheath draped over ferrite cores acts as a shield against photodissolution while still

permitting tunneling-assisted electron flow, from TiO_2 into the ferrite's conduction bands [4]. Stability becomes a linchpin when tackling waste streams that host a mélange of molecular species and often contain chloride or sulfate ions competing for reactive radicals; if the interfacial layer collapses midway catalytic activity nosedives and residual pollutants linger. Visible-light-driven designs push the envelope further enabling degradation without the crutch of UV illumination. For example, the ternary nanocomposite g-C_3N_4/CdS/$CuFe_2O_4$ has demonstrated up to 85 % removal of agents such as AZT, within a 90-minute window [23]. The intricate heterojunction scaffold channels charge along a web of routes that reconfigure with the wavelength of incoming light simultaneously igniting oxidative and reductive pathways at separate locales while exploiting the distinct spectral windows of each constituent. Although CdS-based platforms are plagued by photocorrosion and the specter of heavy-metal leaching under operation the underlying concept deliberately pairing narrow-bandgap and wide-bandgap semiconductors with magnetic ferrites offers a roadmap toward safer composites built entirely from environmentally benign building blocks. In practice the speed at which pollutants are decomposed inevitably hinges on the pollutant's concentration, to the amount of catalyst applied. High dye loading with a low catalyst mass makes the dye molecules themselves gobble up photons cutting the depth that light can travel a phenomenon called the filter effect, which in turn damps photogeneration rates inside the catalyst [28]. Such uniform dispersion alleviates mass-transfer constraints ensuring pollutants encounter sites, throughout the reactor rather than being trapped in aggregated clusters that are shielded from irradiation. Moreover, tailoring the architecture such as coating ferrite cores with mesoporous TiO_2 shells simultaneously enlarges the accessible surface and boosts permeability, for larger pollutant molecules that would otherwise diffuse sluggishly toward the reactive zones [7]. When photocatalytic conditions are optimal reaction intermediates tend to accumulate fleetingly before they undergo complete mineralization. Certain intermediates may adsorb tenaciously onto the catalyst surface creating a blockage risk if they are not promptly removed by oxidation steps; designing the system for a high turnover frequency diminishes this fouling propensity. Tuning the illumination wavelengths and intensity profiles throughout treatment cycles can speed up the breakdown of intermediates; for example, alternating UV-rich phases with phases leverages the differing dominance of reactive oxygen species across the spectrum and capitalizes on the responsiveness of multicomponent composites [34]. Longer operational lifespans directly enhance feasibility for large-scale deployments such as municipal wastewater plants or decentralized rural installations. Magnetic recovery also reduces reliance on filtration which is prone, to clogging when handling high-turbidity influents loaded with organic matter and suspended solids[4]. So by using ferrite/TiO_2 catalysts that can be magnetically pulled out after each cycle fresh particulate pollutants stay out of the treated water a sustainability win, over powders that must be replaced after a short

lifespan. Embedding SiO_2 layers helps balance accessibility with chemical robustness keeping performance over many cycles close, to the initial output[34]. Still design trade-offs linger: raising coercivity by tweaking the ferrite composition improves retrievability. It can provoke lingering aggregation because residual magnetization remains once the particles leave the magnetic field[9]. Lowering coercivity eases redispersion before the cycle but it may hinder recovery efficiency in large-scale setups unless strong external magnetic gradients are applied to pull all active material out of solution quickly. Striking a balance between constraints and photocatalytic metrics still unfolds as an iterative back-and-forth, guided by both field trials and tightly controlled laboratory experiments. Consequently, whether the target molecule is a chromophoric azo dye of textile effluents or a robust pharmaceutical contaminant from hospital wastewater embedding magnetic ferrites, within TiO2 matrices yields a durable effective remediation sustaining photocatalytic activity while enabling a facile post-treatment separation. By weaving the adsorption perks inherent to ferrite surface chemistry with the electronic boons of engineered heterojunctions and grounding the whole architecture in morphologies that stay well-dispersed in water ferrite/TiO_2 nanocomposites emerge as a multipurpose toolkit, for breaking down organic pollutants across a panoply of environmental scenarios while sidestepping steep operating costs and secondary-contamination pitfalls [10, 20, 34].

6.2 Photocatalytic Generation of Hydrogen

Photocatalytic hydrogen production, with ferrite/TiO_2 nanocomposites blends the light-driven activity of a semiconductor with the benefit of magnetic recovery so water can be split and the catalyst reclaimed in the same step. The process hinges on exciting TiO_2: electrons are promoted into the conduction band (E_CB) where they reduce protons to hydrogen while the complementary holes left in the valence band (E_VB) oxidize water or any sacrificial agents present. In a TiO_2 system this two-half-reaction cycle is often thwarted by fast electron-hole recombination and a narrow spectral window. Linking the system with ferrites such as $NiFe._2O_4$, $CoFe_2O_4$ or $ZnFe_2O_4$ offers a route around those limitations. It does so by forming heterojunctions that boost charge separation and depending on the ferrite's composition can push absorption further into the visible spectrum[35, 36]. Band-edge positions are crucial: the absolute electronegativity χ of each component, with its band gap E_g sets the conduction- and valence-band energies through established relations.

$$E_{\mathrm{CB}} = \chi - E_C - \frac{E_g}{2}$$
$$E_{\mathrm{VB}} = E_{\mathrm{CB}} + E_g$$

Here E_C denotes the free-electron energy on the hydrogen scale 4.5 eV [16]. In a $NiFe_2O_4/TiO_2$ heterojunction $NiFe_2O_4$ with $\chi = 4.65$ eV interfaced to TiO_2 with $\chi = 5.8$ eV the resulting offset nudges

electrons, from TiO_2 into the ferrite under illumination, which in turn slows recombination and keeps the reduction potentials aligned for H_2 evolution. The specific material synthesis pathway chosen can markedly shape these benefits. Sol-gel derived $CoFe_2O_4/TiO_2$ has shown a stable hydrogen-production output over many visible-light cycles a robustness that stems from its uniformly dispersed particles and a meticulously tuned interfacial contact[37, 38]. Hydrothermal routes on the hand can produce inverse-spinel ferrites such, as $NiFe_2O_4$; their nanometer-scale particles enlarge the surface area and pile up reaction sites thereby boosting both photonic absorption and proton-reduction activity. Researchers have begun inserting an interlayer most often SiO_2 between magnetic cores and TiO_2 shells to guard against photo dissolution while still preserving the short-range tunneling needed for charge carriers to reach the reactive zones where water oxidation occurs[39, 40]. By tuning the design levers along these axes ferrite/TiO_2 nanocomposites shift from merely viable to potentially superior candidates for large-scale photocatalytic hydrogen generation marrying renewable-energy conversion, with simple catalyst handling and recyclability [16].

In conclusion, Ferrite/TiO_2 nanocomposites present a highly promising and rationally designed platform for photocatalytic hydrogen generation. By leveraging visible-light absorption through the ferrite and enabling superior charge separation via engineered heterojunctions, these materials translate the proven principles of enhanced photocatalytic remediation directly to the critical challenge of sustainable fuel production.

7. Conclusion

Ferrite–TiO_2 nanocomposites are carving out a niche as a promising suite of multifunctional materials that fuse magnetic behavior with photocatalytic action to meet pressing environmental demands. By stitching magnetic ferrite nanoparticles and the semiconductor titanium dioxide these hybrids can swiftly dismantle recalcitrant organic pollutants in water and air and they can be recovered with a simple magnetic pull. The cooperative interaction, between the TiO_2 phases boosts charge-carrier separation slashing the recombination losses that typically throttle photocatalytic performance in ordinary semiconductor systems. In practice the gain translates into a bump in quantum yields and a sped-up demolition of pollutants particularly when heterojunctions are painstakingly engineered to align the bands just right and to ease the flow of charge, across the interface.

In water-treatment settings ferrite/TiO_2 composites have proven effective at breaking down synthetic dyes, pharmaceuticals and other tenacious organics thanks, to their boosted adsorption capacity and lengthened charge-carrier lifetimes. Their magnetic retrievability curtails secondary-pollution concerns stemming from powder loss or filter fouling allowing the catalysts to be recovered and reused

across cycles. Likewise in hydrogen generation these nanocomposites exploit heterojunction-driven charge separation and visible-light absorption to lift hydrogen evolution rates while preserving catalyst stability and recyclability. When magnetism and photocatalysis dance together they dictate how particles spread out and how they grab light and that choreography bumps, up the system's efficiency.

At the end of the day ferrite/TiO_2 nanocomposites serve as a toolkit that can outmaneuver the built-in constraints of classic photocatalysts pairing amplified light-induced reactivity with an effortlessly recoverable magnetic handle. Their knack for being tuned to a spectrum of pollutants operating conditions and illumination regimes makes them attractive prospects for large-scale, low-energy water cleaning, air-quality management and the production of hydrogen. As the field pushes these composites forward, they are set to play a substantive part in the worldwide drive, to tame environmental pollution and foster clean-energy solutions.

Conflicts of Interest: There is no conflict of interest.

References

[1] M. Suneetha *et al.*, "Green Visible light catalysis for dye effluent Degradation with special reference Alizarin red and Antibacterial activity using $SrFe_{12}O_{19}/TiO_2/SiO_2$/GO Nanocomposite," in *International Conference on Bio-Based Environment for Sustainable Territory (ICBEST 2024)*, ed: Atlantis Press, 2025, pp. 195-220 , 94-6463-648-3.

[2] A. Khan *et al.*, "$FeSe_2/TiO_2$ heterostructure as an efficient photocatalyst and their electrochemical energy storage applications," *Materials Chemistry and Physics,* vol. 303, pp. 127793 . 0254-0584, 2023.

[3] E. T. Helmy, U. A. Soliman, A. M. Elbasiony, and B.-S. Nguyen, "CuCe-ferrite/TiO_2 nanocomposite as an efficient magnetically separable photocatalyst for dye pollutants decolorization," *Topics in Catalysis,* vol. 66, no. 1, pp. 53-63, 2023.

[4] R.-G. Ciocarlan *et al.*, "Ferrite/ TiO_2-nanocomposites as Z-scheme photocatalysts for CO_2 conversion: Insight into the correlation of the Co-Zn metal composition and the catalytic activity," *Journal of CO_2 Utilization,* vol. 36, pp. 177-186, 2020.

[5] K. Duan *et al.*, "A facile route to synthesize n-SnO_2/p-$CuFe_2O_4$ to rapidly degrade toxic methylene blue dye under natural sunlight," *RSC advances,* vol. 12, no. 26, pp. 16544-16553, 2022.

[6] A. Zielinska-Jurek *et al.*, "Design and application of magnetic photocatalysts for water treatment. The effect of particle charge on surface functionality," *Catalysts,* vol. 7, no. 12, p. 360, 2017.

[7] E. B. Lashkaryani, B. Kakavandi, R. R. Kalantary, A. J. Jafari, and M. Gholami, "Activation of peroxymonosulfate into amoxicillin degradation using cobalt ferrite nanoparticles anchored on graphene ($CoFe_2O_4$/ Gr)," *Toxin Reviews,* 2021.

[8] P. Shandilya, S. Sambyal, R. Sharma, A. Kumar, and D.-V. N. Vo, "Recent advancement on ferrite based heterojunction for photocatalytic degradation of organic pollutants: a review," *Ferrite: Nanostructures with tunable properties and diverse applications,* pp. 121-161, 2021.

[9] D. Balatskiy, Y. Budnikova, S. Bratskaya, and M. Vasilyeva, "TiO_2-$CoFe_2O_4$ and TiO_2-$CuFe_2O_4$ composite films: A new approach to synthesis, characterization, and optical and photocatalytic properties," *Journal of Composites Science,* vol. 7, no. 7, p. 295, 2023.

[10] M. Golshan, B. Kakavandi, M. Ahmadi, and M. Azizi, "Photocatalytic activation of peroxymonosulfate by TiO_2 anchored on cupper ferrite (TiO_2/ $CuFe_2O_4$) into 2, 4-D degradation: Process feasibility, mechanism and pathway," *Journal of hazardous materials,* vol. 359, pp. 325-337, 2018. [Online]. Available: https://www.sciencedirect.com/science/article/abs/pii/S0304389418305090?via%3Dihub.

[11] E. T. Helmy, M. A. Ayyad, M. A. Ali, H. G. Mohamedbakr, and J. H. Pan, "Biochemical, Histological Changes, Protein Electrophoretic Pattern, and Field Application of CuPb–Ferrite/TiO_2 Nanocomposites for Controlling Terrestrial Gastropod Eobania vermiculata (Müller)," *Journal of Agricultural and Food Chemistry,* vol. 71, no. 17, pp. 6626-6634, 2023.

[12] N. I. Zouli, "Photodegradation of a Broad-Spectrum Antibiotic Azithromycin Using H_2O_2 under Ultraviolet Irradiation," *International Journal of Molecular Sciences,* vol. 25, no. 12, pp. 6702 , 1422-0067, 2024.

[13] T. Rahmiati, C.-C. Chen, S. A. Saad, N. Eko, and A. Apriana, "Surface Character of Magnetic Ce-doped TiO_2 for Photocatalytic Performance Enhancement," *Recent in Engineering Science and Technology,* vol. 1, no. 01, pp. 1-6, 2023.

[14] H. Ma and C. Liu, "A mini-review of ferrites-based photocatalyst on application of hydrogen production," *Frontiers in Energy,* vol. 15, no. 3, pp. 621-630, 2021.

[15] R. Suresh, S. Rajendran, P. S. Kumar, D.-V. N. Vo, and L. Cornejo-Ponce, "RETRACTED: Recent advancements of spinel ferrite based binary nanocomposite photocatalysts in wastewater treatment," *Chemosphere,* vol. 274, p. 129734, 2021. [Online]. Available: https://www.sciencedirect.com/science/article/pii/S0045653521002034?via%3Dihub.

[16] H. C. T. Firmino *et al.*, "Nickel ferrite/TiO_2 nanofibrous composite: enhanced photocatalytic dye degradation under visible light," *Materials Research,* vol. 27, p. e20230391, 2024.

[17] S. Yousefi-Mohammadi, M. Movahedi, and H. Salavati, "MnCo–Ferrite/TiO_2 composite as an efficient magnetically separable photocatalyst for decolorization of dye pollutants in aqueous solution," *Surfaces and Interfaces,* vol. 11, pp. 91-97, 2018.

[18] M. Ahmadmoazzam, H. Akbari, A. Adibzadeh, S. Pourfadakari, and H. Akbari, "Visible-light-driven TiO_2/ Fe_2O_3/Chitosan nanocomposite with promoted photodegradation of meropenem and imipenem antibiotics by peroxymonosulfate," *Environmental Technology,* vol. 45, no. 17, pp. 3456-3467, 2024.

[19] S. Rohilla, "Rietveld refinement and structural characterization of TiO_2/$CoFe_2O_4$nanocomposites," in *IOP Conference Series: Materials Science and Engineering* vol. 872, ed: IOP Publishing, 2020, pp. 012171 , 1757-899X.

[20] S. Das *et al.*, "Structural, magnetic, and dielectric behaviour of Ce^{3+} doped Ni-Zn ferrite/TiO_2 magneto-dielectric nanocomposites," *Applied Physics A,* vol. 131, no. 10, pp. 1-21, 2025.

[21] R. Peymanfar and M. Rahmanisaghieh, "Preparation of neat and capped BaFe2O4 nanoparticles and investigation of morphology, magnetic, and polarization effects on its microwave and optical performance," *Materials Research Express,* vol. 5, no. 10, p. 105012, 2018.

[22] J. Zhao *et al.*, "Lanthanum and neodymium doped barium ferrite-TiO_2/MCNTs/poly (3-methyl thiophene) composites with nest structures: preparation, characterization and electromagnetic microwave absorption properties," *Scientific reports,* vol. 6, no. 1, p. 20496, 2016.

[23] S. Das, G. C. Nayak, S. K. Sahu, P. C. Routray, A. K. Roy, and H. Baskey, "Titania-coated magnetite and Ni-ferrite nanocomposite-based RADAR absorbing materials for camouflaging application," *Polymer-Plastics Technology and Engineering,* vol. 54, no. 14, pp. 1483-1493, 2015.

[24] L. Saini, M. K. Patra, R. K. Jani, G. K. Gupta, A. Dixit, and S. R. Vadera, "Tunable Twin Matching Frequency (f m1/f m2) Behavior of Ni1− xZnxFe2O4/NBR Composites over 2–

12.4 GHz: A Strategic Material System for Stealth Applications," *Scientific Reports,* vol. 7, no. 1, pp. 44457 , 2045-2322, 2017.

[25] H. Gong, "Photodegradation of pharmaceuticals with a recyclable catalyst $CoFe_2O_4/TiO_2$ in aqueous phase," 2018.

[26] H. O. U. Cuiling, L. I. Tiehu, Z. Xueyun, and C. Xiaowen, "Double-layer Electromagnetic Wave Absorber Based on Carbon Nanotubes Doped with La $(NO_3)_3$ and Fe_3O_4 Nanoparticles," *Materials Science,* vol. 23, no. 3, pp. 200-204, 2017.

[27] S. Rohilla, "Rietveld refinement and structural characterization of TiO2/CoFe2O4nanocomposites," 2020, vol. 872: IOP Publishing, pp. 012171 , 1757-899X.

[28] A. A. Alamri *et al.*, "Green magnetically separable molluscicide Ba–Ce–Cu ferrite/TiO2 nanocomposite for controlling terrestrial gastropods Monacha Cartusiana," *Scientific Reports,* vol. 15, no. 1, p. 2888, 2025. [Online]. Available: https://www.nature.com/articles/s41598-025-85730-8.pdf.

[29] R. Peymanfar, F. Norouzi, and S. Javanshir, "A novel approach to prepare one-pot Fe/PPy nanocomposite and evaluation of its microwave, magnetic, and optical performance," *Materials Research Express,* vol. 6, no. 3, p. 035024, 2018.

[30] S. S. Rasooly, M. Anwer, and G. Tsnim, "A review on treatment methods for pesticide contaminated water," *Journal of Environmental Science e, Toxicology and Food Technology,* vol. 16, p. 24, 2022.

[31] A. Rahimi, M. H. Zonoozi, R. Rahimi, and B. Zahabiyoun, "Photocatalytic activity of GO-doped bismuth-based photocatalyst for Methyl Orange decolorization under visible light irradiation," *Desalination and Water Treatment,* vol. 180, pp. 360-369, 2020.

[32] A. M. Elbasiony, A. A. Alamri, U. A. Soliman, H. G. Mohamedbakr, A. M. Wahba, and E. T. Helmy, "Green synthesis of N, B co-doped TiO2 nanoparticles with enhanced photocatalytic and antioxidant activities," *Journal of the Taiwan Institute of Chemical Engineers,* pp. 105626 , 1876-1070, 2024.

[33] E. E. Zaghloul, A. S. Amin, M. A. Diab, A. Elsonbati, and M. Ibrahim, "Removing 2, 4-dichlorophenoxyacetic acid (2, 4-D) from polluted water using zinc ferrite nanoparticles," *Egyptian Journal of Chemistry,* vol. 63, no. 4, pp. 1411-1428, 2020.

[34] P. Jiang, Y. Yu, and K. Li, "Hydrophilic TiO2/ MWCNT/PVDF membrane for enhanced photodegradation of methyl orange in water," *Fullerenes, Nanotubes and Carbon Nanostructures,* vol. 31, no. 12, pp. 1185-1191, 2023.

[35] C. Mahala, M. D. Sharma, and M. Basu, "2D nanostructures of CoFe2O4 and NiFe2O4: efficient oxygen evolution catalyst," *Electrochimica Acta,* vol. 273, pp. 462-473 , 0013-4686, 2018.

[36] O. y. m. N. Avcı, L. Sementa, and A. Fortunelli, "Mechanisms of the oxygen evolution reaction on NiFe2O4 and CoFe2O4 inverse-spinel oxides," *ACS catalysis,* vol. 12, no. 15, pp. 9058-9073 , 2155-5435, 2022.

[37] K. M. Gopalakrishnan, R. Ragul, K. Vallarasu, R. Anitha, and V. Vijayalakshmi, "Exploring CoFe 2 O 4/TiO 2 NCs for high-efficiency UV-driven organic dye degradation," *Journal of Materials Chemistry C,* vol. 13, no. 42, pp. 21561-21573, 2025.

[38] M. Sahni *et al.*, "Investigating the performance of CoFe2O4/ TiO2 nanomaterial as multifunctional cathode catalyst for simultaneous dye degradation and oxygen reduction in microbial desalination cell," *Desalination,* vol. 587, pp. 117958 , 0011-9164, 2024.

[39] H. K. Channi and P. Kumar, "Spinel and Inverse Spinel Ferrites for Environmental Remediation," in *Spinel and Inverse Spinel Ferrites*: Chapman and Hall/CRC, 2025, pp. 130-149 , 1032665653.

[40] J. Tan, W. Zhang, and A.-L. Xia, "Facile synthesis of inverse spinel NiFe2O4 nanocrystals and their superparamagnetic properties," *Materials Research,* vol. 16, pp. 237-241 ,1516-1439, 2013.